

DUPLEX 2205 / UNS S32205 / DIN 1.4462

Ferritic-austenitic stainless steel

2205 Data Sheet

Introduction

2205 is the most widely used duplex stainless steel grade. It complies excellent corrosion resistance and high strength. 2205 is not generally suitable for use at temperatures above 300°C as it suffers from precipitation of brittle micro-constituents, nor below -50°C because of its ductile-to-brittle transition. It also has high resistant to stress and provides a low level of thermal expansion.

Chemical Composition (Typical)

Element	Limits	
	min	max
Carbon	0.000	0.030
Manganese	0.000	2.000
Silicon	0.000	1.000
Phosphorus	0.000	0.030
Sulphur	0.000	0.020
Chromium	21.000	23.000
Molybdenum	2.500	3.500
Nickel	4.500	6.500
Nitrogen	0.080	0.200
Iron	Remainder	

Mechanical Properties (typical)

Parameter	Value
Yield 0.2 % (ksi/Mpa), Min	450
Tensile (ksi/Mpa), Min	620
Elongation (% in 50mm), Min	25
Reduction in Area, %	55
Hardness (HB), Max	293

Physical Properties

Parameter	Value
Density (Kg/m ³)	7800
Elastic Modulus (Gpa)	200
Co-eff of Expansion ($\mu\text{m}/\text{m}/^\circ\text{C}$)	14.7
Thermal Condc. (W/m.K)	19
Electric Resistivity (n Ω .m)	850

Corrosion Data

Excellent corrosion resistance, better to Grade 316 in most environments. Excellent resistance to localised corrosion including intergranular, pitting and crevice corrosion. The grade is also resistant to chloride stress corrosion cracking at temperatures of up to about 150°C. It mostly perform well in environments which cause premature failure of austenitic grades.

Equivalent Grade Designation

SAF 2205
UNS S32205
BS 318S13
DIN EN 1.4462
Z2.CND22.05.03
SS 2377
X2CrNiMoN 22-5-3

2205 Data Sheet

Available Product Forms

Round, Square, Hexagon & Flat Bars
Seamless / Welded Pipes
Seamless / Welded Tubes
Hot & Cold Rolled Plates & Sheets
Forged Bars
Buttweld Pipe Fittings
Forged Fittings
Ferrule Compression Fittings
Forged Flanges
Valves
Gauges

Common Manufacturing Specifications

ASME SA-182, SA-240, SA-798, SA-790, SA-815
ASTM A182, A240, A276, A479, A480, A798, A790, A815, A928, A988, SAE J405

Alternate to Alloy

904L Better formability is needed, with similar corrosion resistance and lower strength.
2507 Higher resistance to corrosion is required.
6%Mo Higher corrosion resistance required, but with lower strength & better formability.
316L High corrosion resistance & strength not needed. More available & lower cost.

Applications & Industries

Chemical processing, transport and storage
Oil and gas exploration, offshore rigs & Refining
Marine environments
Pulp & paper manufacturing
Pollution control equipment
Chemical process plant

Excellence Inherent

With 3 decade long experience inherited, we aim at providing better solutions for Industrial Piping Sector. Skilled Team, passion drives our *will* to be better with resolute for continous customer & vendor concurrence. We also perceive our duty towards planet for its unconditional support & try to minimise any harm caused due to our activity. For Instance, *We Stay Paperless*

The Information contained in this data sheet is for reference purpose only and actual data may vary from product to product. Complete rely on these values for product design recommended. User will be solely responsible for any failure in intended construction. **FERROBEND™** is trademark Property of **FERROBEND**.



FERROBEND | Industrial Piping Products

#1016 Prasad Chambers Opera House Mumbai 400004 INDIA

Tel : 91 - 22 - 6666 5432 Fax : 91 - 22 - 6636 3375

www.ferrobend.com